Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-01-24-02** **Date: 27-01-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010
Customer's Reference	:	BBMP/EE/BTP/WO/36/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-01-18
Sample ID No	:	2018-01-24-02/01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	25-01-18

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.29	_
2	Finess by Air permeablity method (m^2/kg, Min)	294.7	225m^2/kg, Min
3	Density (gm/cc)	3.13	_
4	Standard Consistency (%)	29.0%	Not specified
5	Initial Setting time	165 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-01-24-02** **Date: 22-02-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010
Customer's Reference	:	BBMP/EE/BTP/WO/36/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-01-18
Sample ID No	:	2018-01-24-02/01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	25-01-18

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	55.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-01-24-02** **Date: 27-01-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010
Customer's Reference	:	BBMP/EE/BTP/WO/36/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	24-01-18
Sample ID No	:	2018-01-24-02/02
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	24-01-18

AEE (VRP) SD

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	389	389	2.6	97.4	90-100
3	20 mm	6814	7203	48.0	52.0	30-70
4	10 mm	5113	12316	82.1	17.9	10-35
5	4.75 mm	2357	14673	97.8	2.2	0-5
6	Pan	327	15000	100.0	0	---

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-01-24-02** **Date: 27-01-18**

Sample ID No : 2018-01-24-02/02

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.1	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.5	
3	Specific Gravity	2.64	_
4	Bulk Density(Loose) (Kg/l)	1.48	_
5	Bulk Density(Compacted) (Kg/l)	1.53	_
6	Water Absorption(%)	0.21	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2018-01-24-02** **Date: 27-01-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010
Customer's Reference	:	BBMP/EE/BTP/WO/36/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-01-18
Sample ID No	:	2018-01-24-02/03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	24-01-18
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	85	85	8.5	91.5	90-100	90-100	90-100	95-100
3	2.36 mm	105	190	19.0	81.0	60-95	75-100	85-100	95-100
4	1.18 mm	193	383	38.3	61.7	30-70	55-90	75-100	90-100
5	600 micron	203	586	58.6	41.4	15-34	35-59	60-79	80-100
6	300 micron	172	758	75.8	24.2	5-20	8-30	12-40	15-50
7	150 micron	198	956	95.6	4.4	0-10	0-10	0-10	0-15
8	Pan	44	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

AEE (VRP) SD

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-01-24-02** **Date: 27-01-18**

Sample ID No : 2018-01-24-02/03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.49	–
2	Specific Gravity	2.54	–
3	Material finer than 75 micron(%)	3.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2018-01-24-02** **Date: 26-01-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010
Customer's Reference	:	BBMP/EE/BTP/WO/36/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-01-18
Sample ID No	:	2018-01-24-02/04
Sample Type	:	Indus
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	25-01-18

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
2	Indus	Fe500	10	0.612	549	627	20.0%	Satisfactory	Satisfactory
3	Indus	Fe500	12	0.884	573	635	19.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-02-05-05** **Date: 07/02/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.

Agency : Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010

Customer's Reference : BBMP/EE/BTP/WO/36/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-02-05-05/01

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	31/01/2018	07/02/2018	149.87 X 150.22 X 150.39	22513	8.157	385.0	17.1	16.8
2	M20 Concrete	M20	31/01/2018	07/02/2018	150.44 X 150.71 X 150.48	22673	8.127	371.8	16.4	
3	M20 Concrete	M20	31/01/2018	07/02/2018	150.33 X 150.22 X 149.83	22583	8.197	381.6	16.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-02-05-05** **Date: 28/02/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.

Agency : Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010

Customer's Reference : BBMP/EE/BTP/WO/36/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-02-05-05/02

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	31/01/2018	28/02/2018	150.47 X 150.44 X 150.68	22637	8.138	536.5	23.7	23.7
2	M20 Concrete	M20	31/01/2018	28/02/2018	149.85 X 150.22 X 149.77	22510	8.149	529.0	23.5	
3	M20 Concrete	M20	31/01/2018	28/02/2018	150.49 X 150.19 X 150.21	22602	8.182	540.2	23.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-02-05-05** **Date: 08/02/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.

Agency : Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010

Customer's Reference : BBMP/EE/BTP/WO/36/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-02-05-05/03

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	01/02/2018	08/02/2018	149.85 X 150.33 X 150.47	22527	8.214	506.9	22.5	22.8
2	M20 Concrete	M20	01/02/2018	08/02/2018	150.31 X 150.49 X 150.64	22620	8.195	522.5	23.1	
3	M20 Concrete	M20	01/02/2018	08/02/2018	150.01 X 149.85 X 150.11	22479	8.167	514.8	22.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-02-05-05** **Date: 08/02/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at A K Colony Yelumandamma Badavane, KNV 1st Stage and 2nd Stage in Ward No.10 (Doddabommasandra),Vidyaranyapura Sub Division.

Agency : Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010

Customer's Reference : BBMP/EE/BTP/WO/36/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-02-05-05/03

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/02/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	01/02/2018	08/02/2018	151.11 X 149.87 X 150.33	22647	8.198	373.7	16.5	16.9
2	M20 Concrete	M20	01/02/2018	08/02/2018	150.29 X 150.47 X 149.58	22614	8.144	389.0	17.2	
3	M20 Concrete	M20	01/02/2018	08/02/2018	150.44 X 150.90 X 150.31	22701	8.168	385.9	17.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AEE (VRP) SD

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****